

**FICHA TECNICA / DATA SHEET**

<b>Composition / Composición</b>	55% NYLON 45% POLYURETHANE
<b>Thickness / Grosor</b>	0,8 MM +/- 5%
<b>Width / Ancho</b>	140 CM +/- 3%

PARAMETER	TEST METHOD	RESULT	
<b>Tear Strenght</b> <b>Resistencia al Desgarro</b>	EN 13571:2001	ALONG ACROSS	42N 49N
<b>Abrasion Resistance</b> <b>Resistencia a la Abrasión</b>	EN 13520:2001	DRY > 60000 cycles	
<b>Water Vapour Permeability WVP</b> <b>Permeabilidad al Vapor de Agua</b>	EN 13515:2001	10.60 (mg/cm2.h)	
<b>Water Vapour Absorption WVA</b> <b>Absorción de Vapor de Agua</b>	En 13515:2001	1.66 (mg/cm2)	
<b>Color Fastness to Perspiration</b> <b>Solidez del Color a la Transpiración</b>	ISO 105-E04:2013	ACID ALKALINE	4 - 5 grade
<b>Color Fastness To Rubbing</b> <b>Solidez del Color al Frote</b>	ISO 17700:2004 met A.	DRY 500 cycles	4 - 5 grade
<b>pH Value in Textile</b> <b>Valor de pH en Textil</b>	ISO 3071:2005	6,0 PASS	
<b>REACH COMPLIANCE</b>	SVHC (173) Substances	PASS	